


Viscosity

Date: 18/06/2019

Product: sirosuc 67 - PF003

T (°C)	viscosity (cP) (mPa.s)	rotation speed	spindle
15,0	388,8	25	1
16,1	352,0	25	1
17,0	328,3	30	1
17,9	306,7	30	1
18,9	284,3	30	1
19,8	266,0	30	1
21,0	246,5	40	1
21,8	232,0	40	1
22,8	216,3	40	1
24,0	200,3	40	1
25,0	190,2	50	1
26,1	177,8	50	1
26,9	169,2	50	1
28,0	164,0	60	1
29,9	149	60	1
32,6	137,3	70	1
34,9	128,4	70	1
38,1	119,0	80	1
39,9	111,5	80	1
42,4	108,3	90	1
44	103,4	90	1
44,8	100,8	90	1
46,5	96,11	90	1
50,1	90,1	100	1
51	87,8	100	1
54,1	85,91	115	1
56	83,00	120	1
57,5	79,92	120	1
60	74,92	120	1
62,1	73,38	130	1
64	70,08	130	1
64,8	68,69	130	1
68,7	66,4	150	1
70,3	63,93	150	1
70,9	62,8	150	1



Evelyne Deprez
QA/QC assistant